



TIGHT BUFFER PLENUM FIBER OPTIC CABLE PRODUCT SPECIFICATION 99XXX26BRZSXNP

This document establishes the specification requirements for a distribution fiber optic cable. This cable construction consists of multimode fibers in a distribution tight-buffered design with a plenum rated jacket. It contains test values for all-important mechanical, optical, and environmental parameters and as such, is the basis for all-incoming inspection and acceptance.

1.0 OVERALL CABLE CONSTRUCTION

1.1 Tight Buffered Fiber

Dimension: 900µm, nominal.

Tight buffered fiber color code: 1-blue, 2-orange, 3-green, 4-brown, 5-slate, 6-white, 7-red, 8-black, 9-yellow, 10-violet, 11-rose, and 12-aqua.

1.2 Sub-unit consists of aramid yarns that are pulled in with the tight-buffered fibers under a sub-unit jacket that is uniquely identified.

1.3 Cable strength Member

Fiberglass Epoxy Rod (dielectric)

An up coat of plenum material (if necessary per construction for symmetry)

1.4 Cable Core

Sub-units and fillers (if needed) are stranded around the CSM, using reverse oscillation.

A non-wicking and non-hygroscopic tape is applied longitudinally with a nominal 25% overlap.

Binder yarns are applied over the core tape.

1.5 Outer Sheath

Orange plenum rated jacket (or color per customer request)

1.6 Cable Markings

Indent printed: CCT GROUP99, FIBER OPTIC CABLE, # of fibers-62.5/125, MM/YY (month and year of manufacture), OFNP C(ETL)US sequentially meter marked. Special print as required by customer.

Special print as required by customer.

1.7 Nominal Cable Dimensions & Weights

CCT Part Number	No. of Fibers	Cable OD (mm)	Cable OD (in.)	Weight KG/KM	Weight LB/1000ft
9901826BRZSFNP	18	13.9	0.546	173	116
9902426BRZSFNP	24	13.9	0.546	170	114
9903626BRZSFNP	36	16.7	0.656	253	170
9904826BRZSLNP	48	16.1	0.634	225	151
9906026BRZSLNP	60	17.7	0.696	275	185
9907226BRZSLNP	72	19.2	0.756	334	224



2.0 FIBER CHARACTERISTICS - Physical Parameters (nominal)

<u>Fiber Type</u>	<u>Multimode Graded Index</u>
Maximum Attenuation @ 850/1300nm*	3.5 /1.5 dB/km
Minimum Bandwidth @850/1300nm	160/500MHz-km
Core Diameter, nominal	62.5 ± 3 μm
Cladding Diameter	125.0 ± 1.0 μm
Primary Coating Diameter	245 ± 10 μm
Cladding Non-circularity	<2%
Core/Clad Offset	3 μm
Zero Dispersion Wavelength	1320-1365nm
Numerical Aperture	0.275 ± .015
Group Refractive Index @ 850/1300nm	1.496/1.491
Proof Test	100 kpsi

**Measured attenuations on shipping reels will not exceed the nominal values by .75dB/km.*

3.0 MECHANICAL & ENVIRONMENTAL PERFORMANCE

Maximum Tensile Load for:	Impact Resistance: 25 Impacts (min.)
Installation: 2700N / 607lbf	Flexing, ±90°: 25 Cycles (min.)
Long Term: 890N / 200lbf	Temperature Rating:
Minimum bending radius:	Operation: -20°C to +85°C
Loaded: 20 x diameter	Installation: 0°C to +75°C
Unloaded: 10 x diameter	Storage: -40°C to +85°C
Crush Resistance: 220N/cm	

4.0 PREPARATION FOR DELIVERY

The cable shall be packaged to preclude the inducement of damage due to handling and transportation, and shall be in accordance with the best commercial practices available.

5.0 APPLICABLE DOCUMENTS

Reference Documents:	TIA/EIA FOTP Standards 455
	Color Coding of Fiber Optic Cables TIA/EIA-598
	UL 910
	GR-409-CORE